



NISHKA ALLIANCE LLP.

**INCI NAME: Cyclopentasiloxane(and)Dimethiconol(and) Dimethicone Crosspolymer.
NISH 1006**

NISH 1006 is a blend of Dimethiconol and silicone elastomer in cyclopentasiloxane.

Benefits:

- It provides silky, smooth, non-greasy and matte-finish.
- It modifies texture as a thickening agent, reducing tackiness in formulations
- It helps to fill in pores and fine lines.
- It spreads easily and acts as a carrier for actives, pigments and fragrances.
- It is a good film former.
- It is incorporated in haircare products for shine and heat protection.

Applications:

- Skincare.
- Haircare.
- Color Cosmetics.

Characteristic Properties:

- | | |
|----------------------------|-------------------------|
| • Appearance | Clear colorless liquid. |
| • Active content | 100% |
| • Refractive index at 25°C | 1.400 |
| • Specific gravity at 25°C | 0.98 |
| • Viscosity at 25°C | 3500cst |

These figures are only intended as a guide and should not be used in preparing specifications.

Product Safety, Handling and Storage

For product safety & handling read material safety data sheets. When stored at or below 25°C (77°F) in the original unopened containers, this product has a usable life of 36 months from the date of production. It should be stored in cool and dry place in dust-free environment.

Packaging:

Available in 200kg drums and 20kg carboys.

How to use

NISH 1006 may be used alone or blended with other cosmetic fluids to be incorporated in cosmetic formulations. It can be incorporated in oil phase in closed system at a temperature range of 70-75°C while manufacturing creams or lotions.

Recommended dosage is 1.0 - 5.0%

Important

The data and statements contained herein are based on our research and/or the research of others, and are believed to be accurate. No guarantee of their accuracy is made however, and unless expressly stated in a written contract, the product(s) discussed herein are sold without conditions or warranties, expressed or implied. Purchasers are advised to make their own tests to determine the suitability of this product for their particular purposes. Nothing contained herein shall be construed as a recommendation to use or as a license to operate under or to infringe on any existing patent